

PRIMERTABELLE

Primer-Anwendungstabelle	BUTYL		SILICON		HYBRID	PUR	ACRYL
	EGOBON EGOFERM EGOPOL Serie	EGOSILICON 100er Serie (Acetat)	EGOSILICON 300er Serie (Oxim)	EGOSILICON 400er Serie (Alkoxy)	EGO SMP HYBRID Serie	EGOFLEX Serie	EGOCRYL Serie
Acrylglas (PMMA)	✓	*	FML*/HR	FML*/HR	✓/***	✗	✗
Acryllack	✓	FML/✓	FML/✓**	FML/✓	✓/***	✓/HR	✓
Alkydharzlack	✓	✓	✓**	✓	✓/***	HR	✓
Aluminium blank	✓	FML/***	FML/***	FML/***	HR/✓/***	***	✗
Aluminium eloxiert	✓	FML/✓	FML/✓	FML/✓	HR/✓/***	HR	✗
Beton	PRO/ECO	✗	FDf	FDf	FDf/✓/***	PUR	A*H ₂ O
Bitumen	PRO	✗	✗	✗	✗	✗	✗
Blei	✓/PRO	✗	FML	FML	HR/***	HR/***	✗
Chrom	✓	✗	FML	FML	✓/HR	✗	✗
DD-Lack	✓	✓	✓**	✓	✓/***	✓/HR	✓
Dispersionsfensterlack	✓	FML/✓	✓**	✓	✓/***	✓/HR	✓
Dispersionsfassadenfarbe	✓	✗	FML/FDf/***	FML/FDf/***	✓	✓/HR	✓
Edelstahl (V2A) (V4A)	✓	FML/HR	FML/HR	FML/HR	HR/✓/***	HR	✗
Eisen	✓/PRO	✗	FML	FML	HR/***	HR	✗
Emaillie	✓	✓	✓	✓	✓	HR	✗
Epoxidharzlack	✓	✓	✓	✓	✓	✓/HR	✗
Faserzement	PRO/ECO	✗	FDf	FDf	FDf	PUR	A*H ₂ O
Fliesen glasiert	✓	✓	✓	✓	✓	HR	✗
Fliesen unglasiert	✓/PRO/ECO	✗	FDf	FDf	✓	PUR	✓
Glas	✓	✓	✓	✓	✓	✗	✗
Kunststein	✓	✗	FDf/***	✗	✓/***	✓/HR/***	✓/A*H ₂ O
Kupfer	✓	✗	FML**	FML	✗	HR/***	✗
Lasuranstrich	✓	FML	FML/✓	FML/✓	✓	✓/HR	✓
Melaminharz	✓	HR/✓	HR/✓	HR/✓	HR/✓/***	HR	✓
Messing	✓	✗	FML**	FML	HR/***	HR/***	✗
Naturstein	✗	✗	FDf/***	✗	FDf/***	✓/HR/***	✗
Polycarbonat (PC)	✓	FML*/HR	FML*/HR	FML*/HR	✓/***	✗	✗
Polyester (GFK)	✓	FML/HR	FML/HR	FML/HR	✓/***	HR	✗
Porenbeton	PRO/ECO	✗	FDf	FDf	FDf/***	PUR	A*H ₂ O
Pulverlackbeschichtung	✓	FML/HR	FML/HR	FML/HR	HR/✓/***	HR	✗
PVC hart	✓	FML	FML	FML	✓/***	PUR	✗
Stahl blank	✓	✗	FML	FML	HR/✓/***	HR	✗
Stahl verzinkt	✓	✗	FML	FML	HR/✓/***	HR	✗
Styropor	✓/ECO	✗	✓	✓	✓/***	✗	✓
Zinkblech	✓	✗	FML	FML	HR/***	HR	✗
Zinkstaubfarbe	✓	✗	FML	FML	✓/***	HR/***	✓

✓ = Anwendung ohne Primer möglich

✗ = Anwendung nicht empfohlen

* = Primer dünn auftragen und für schnelle Ablüftung sorgen,

da bei Langzeiteinwirkung die Gefahr von Spannungsriss Korrosion besteht.

** = Spaltprodukte gut ablüften lassen

*** = Eigenversuche werden empfohlen

FDf = EGO PRIMER FDf

FML = EGO PRIMER FML

PUR = EGO PRIMER PUR

HR = EGO HAFTREINIGER

PRO = EGO BUTYLPRIMER PRO (lösemittelhaltig)

ECO = EGO BUTYLPRIMER ECO (lösemittelfrei)

A*H₂O = EGOCRYL mit Wasser verdünnen